

Exercise book cover paper

Indicators	Norms			Test method
Fibre mix	TMP – 100%			
Paper weight 1 m ² , g	70±3	80±3	90±3	ISO 536
Breaking Length, MD, km, min.	5,0			ISO 1924-1
Elongation, %, minimum	0,80			
Absolute crosswise tearing resistance, mN, minimum	350			ISO 1974
Opacity, %, minimum	95			GOST 8874
Moisture, %	7,0±1,0			ISO 287
Number of splices in a reel Less than 1 m in diameter 1 m and more in diameter	1 2			By eye
Reel width tolerance, mm	±1,0			
Amount of mill joins	one per 10 reels			

¹ Shade can vary, confirm the shade based on product samples