

Uncoated paper for writing and printing or used for other graphic purposes

Parameters	42 g/m ²	42.5 g/m ²	45 g/m ²	48 g/m ²	48.8 g/m ²	52 g/m ²	55 g/m ²	58 g/m ²
Basis weight, g/m ²	42,0 +/-1	42,5 +/-1	45,0 +/-1	48,0 +/-1	48,8 +/-1	52,0 +/-1	55,0 +/-1	58,0 +/-1
Composition	TMP – 100%							
Bulk, cm ³ /g	1,75 +/- 0,09							
Moisture, %	8,0 +/- 1							
Absolute crosswise tearing resistance, mN	min 220		min 250	min 280		min 290	min 300	min 310
Breaking length in MD, km	min 4,9	min 4,9	min 5,0	min 5,0		min 5,1		
Elongation, %	min 0,70	min 0,75	min 0,80					
Smoothness (Bekk), average on 2 sides, sek	45 +/- 10							
Brightness, %, (R457 C)	60 +/- 1							
Opacity, %	min 90	min 90	min 91	min 93		min 94		min 95
Number of splices	one per 10 reels							

*HS code: 4802611500